

Test laboratory for the fire behavior of building materials, Dipl.-Ing. (FH) Andreas Hoch
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT

PZ-Hoch-140153

for the proof of Fire behaviour according to DIN 4102, part 1

Translation of the German test report – no guarantee for translation of technical terms

company	Junkers & Müllers GmbH Bolksbuscher Straße 27 D-41239 Mönchengladbach
description of samples	-fabric consisting of polyester, with polymer coating and protective coating with pearl pigments on one side- colour: white / silver
name of the material	„TT MEDIATEX JM-AIR EFFECT FR“
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 “schwerentflammbar” according to DIN 4102, part 1
validity of test report	31.01.2019
result	The examined product meets the requirements of class B1 for “schwerentflammbare” (hardly flammable) building materials according to DIN 4102, part 1 (May 1998) , suspended freely or with distance of >40 mm to same or other plain materials.

This test report includes 4 pages and 4 enclosures.

Remark: If the above mentioned building material is not used as product according to MBO § 2, Abs. 9, Ziffer 1, there is no need for a general building supervisory test report.

This test report is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17, Abs. 3).

This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions. This has to be verified by:

- “allgemeine bauaufsichtliche Zulassung” (general building inspectorate approval) or by
- „allgemeines bauaufsichtliches Prüfzeugnis“ (general building inspectorate certificate) or by
- “Zustimmung im Einzelfall” (exceptional approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for non regular building products for the needed proofs of applicability.

This test report must not be published and copied without preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents.

1. Description of test material in condition as delivered

PN 18738: "TT MEDIATEX JM-AIR EFFECT FR"

-fabric consisting of polyester, with polymer coating and protective coating with pearl pigments on one side- colour: white / silver

side A: white side B: silver

characteristic values determined by the test laboratory:

area weight: about 228 g/m² thickness: about 0,36mm

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

The samples were kept in climate chamber 23/50 until they reached constant weight.

3. Arrangement of samples

mounting: freely suspended

#4986: flaming side A in warp direction

#4988: flaming side B in warp direction

#4989: flaming side B in weft direction

4. Date of test CW 06 in 2014

5. Results The test has been examined according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen				Dim.
	Test number	#4986	#4988	#4989	---	
	flaming direction / side	warp / A	warp / B	weft / B	---	
1	<u>Number of specimen arrangement</u> acc. to. DIN 4102/T15, schedule 1	1	1	1	---	
2	<u>Maximum flame height above bottom</u> edge of the specimen	50	60	70		cm
3	Time ¹⁾	0:14	0:21	0:28	---	min:s
4	<u>Burn through / melting</u> Time ¹⁾	0:03	0:04	0:04	---	min:s
	<u>Observations on the back side of the specimen</u>					
5	Flames / Glowing Time ¹⁾	./.	./.	./.	./.	min:s
6	Change of color Time ¹⁾	./.	./.	./.	./.	min:s
7	<u>Falling of burning droplets</u> Start ¹⁾	./.	./.	./.	./.	min:s
8	sporadic falling of burning droplets ²⁾	./.	./.	./.	./.	
9	continuous falling of burning droplets ²⁾	./.	./.	./.	./.	min:s
10	<u>Falling of burning droplets</u> Start ¹⁾	./.	./.	./.	./.	min:s
11	sporadic falling of burning droplets ²⁾	./.	./.	./.	./.	
12	continuous falling of burning droplets ²⁾	./.	./.	./.	./.	

no.	Measurement	Result with the tested specimen				Dim.
		#4986	#4988	#4989	---	
	Test number	#4986	#4988	#4989	---	
	flaming direction / side	warp / A	warp / B	weft / B	---	
13	<u>Afterflame time at the bottom of the sieve (max.)</u>	./.	./.	./.	./.	min:s
14	<u>Impairment of the burner by dropping or falling material:</u> Time ¹⁾	./.	./.	./.	./.	min:s
15	<u>Premature end of test</u> Final occurrence of burning at the specimen ¹⁾	./.	./.	./.	./.	min:s
16	Time of eventually end of test ¹⁾	./.	./.	./.	./.	min:s
17	<u>Afterflame after end of test</u> Time ¹⁾	./.	./.	./.	./.	min:s
18	Number of specimen	./.	./.	./.	./.	
19	Front side of specimen ²⁾	./.	./.	./.	./.	
20	Back side of specimen ²⁾	./.	./.	./.	./.	
21	flame length	./.	./.	./.	./.	cm
22	<u>Afterglow after end of test</u> Time ¹⁾	./.	./.	./.	./.	min:s
23	Number of specimen	./.	./.	./.	./.	
24	<u>Place of appearance</u> Lower half of the specimen ²⁾	./.	./.	./.	./.	
25	Upper half of the specimen ²⁾	./.	./.	./.	./.	
26	Front side of specimen ²⁾	./.	./.	./.	./.	
27	Back side of specimen ²⁾	./.	./.	./.	./.	
28	<u>Density of smoke</u> ≤ 400 % * min	24	34	31	---	% * min
29	> 400 % * min ⁴⁾	./.	./.	./.	./.	% * min
30	Diagram: encl. no.	1	2	3	---	
31	<u>Residual lengths: individual value</u> ³⁾					
	Specimen 1	63	67	47	---	cm
	Specimen 2	51	41	41	---	cm
	Specimen 3	58	48	56	---	cm
	Specimen 4	65	54	58	---	cm
32	<u>Average value, individual test</u> ³⁾	59	53	51	---	
33	Photo of specimen in enclosure no.	1	2	3	---	
34	<u>Flue gas temperature</u>	118	120	120	---	°C
35	Maximum of average value Time ¹⁾	09:11	09:44	09:11	---	min:s
36	Diagram: encl. no.	1	2	3	---	
37	Remarks: - none -					

¹⁾ indication of times: from the begin of testing procedure

²⁾ checked off if applicable

³⁾ indication of carrier/foam layer separated in case of fire-proofing agents

⁴⁾ very strong development of smoke

6. Explanations concerning the testing procedure

There were no additional tests proceeded because of the residual length of more than 45 cm.

7. Summary of results and additional establishments to Fire Behaviour

lineo.	measurement	Result with the tested specimen				dimen sion
	test-no.	#4986 warp / A	#4988 warp / B	#4989 weft / B	---	
1	residual length	59	53	51	---	cm
2	max. smoke temperature	118	120	120	---	°C
3	density of smoke - integral	24	34	31	---	%min
4	remarks: -none-					

According to DIN 4102, part 1, "schwerentflammbare" (hardly flammable) building materials must meet the requirements of class B2.

Pursuant to additional tests in the ignitability apparatus this can be determined (appendix 4).

8. Special remarks

- This report is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or grounds etc. the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions, washing or cleaning with chemicals.
- This test report is not valid, as soon as the fabric is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, im particular private proprietary rights.
- For legal interests only the German original version is relevant.
- In General Building Inspectorates procedures this test report can be based for
 - regular building materials for the required proof of accordance
 - for not regular building materials for the required proof of applicability

9. Validity

This test report is valid until the mentioned date on page 1. The test report becomes invalid in case the standards on which the tests are based are changed.

Fladungen, 10.02.2014

clerk in charge:



(Dipl.-Ing. (FH) Jürgen Hammer)




Head of the test laboratory:




(Dipl.-Ing.(FH) Andreas Hoch)

„Brandschacht“-test #4986



measurement

4986, Junkers & Müllers, "TT MEDIATEX JM-AIR..." A+K, PN18738
residual length: 59cm, max. smoketemp.:118°C, smoke-Int.:24%/min




„Brandschacht“-test #4988



measurement

4988, Junkers & Müllers, "TT MEDIATEX JM-AIR..." B+K, PN18738
residual length: 53cm, max. smoketemp.:120°C, smoke-Int.:34%/min



„Brandschacht“-test #4989



measurement

**Test for normal flammability
classifying B2 according to DIN 4102**

1. Description of test material in condition as delivered look at page 2
2. Preparation of samples
Out of the material there have been cut samples for the ignitability apparatus.
The samples were kept in a climate 23/50 until they reached constant weight.
3. Arrangement of samples -freely suspended-
Flaming in warp and weft direction / Flaming side A and side B
4. Date of test CW 06 in 2014
5. Results

PN 18738: flaming side A in warp	surface-test						edge-test						Dim
samples no.	1	2	3	4	5	6	1	2	3	4	5	6	
ignition ¹⁾	3	2	32	2	3	--	1	--	--	--	--	--	s
reaching the mark of measurement ¹⁾²⁾	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	s
max. flame height	13	12	10	13	14	--	8	--	--	--	--	--	cm
time	11	11	9	12	13	--	4	--	--	--	--	--	
self cessation of the flames end of afterflame ¹⁾	12	16	14	14	15	--	6	--	--	--	--	--	s
end of glowing ¹⁾	16	./.	16	16	./.	--	./.	--	--	--	--	--	s
flames were extinguished after ¹⁾	./.	./.	./.	./.	./.	--	./.	-/-	-/-	--	--	--	s
smoke development (visual)	heavy						heavy						
dropping of burning material during 20 s ¹⁾	./.	./.	./.	./.	./.	--	./.	--	--	--	--	--	s
Appearance after test: burned out till max. height 13cm x width 2,5cm													

PN 18738: additional tests	edge-test						surface-test						Dim
samples no.	1	2	3	4	5	6	1	2	3	4	5	6	
ignition ¹⁾	1	1	1	--	--	--	3	3	4	--	--	--	s
reaching the mark of measurement ¹⁾²⁾	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
max. flame height	9	5	5	--	--	--	14	14	12	--	--	--	cm
time	5	2	2	--	--	--	11	12	11	--	--	--	
self cessation of the flames end of afterflame ¹⁾	8	3	3	--	--	--	13	14	15	--	--	--	s
end of glowing ¹⁾	./.	./.	./.	--	--	--	16	16	16	--	--	--	s
flames were extinguished after ¹⁾	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
smoke development (visual)	heavy						heavy						
dropping of burning material during 20 s ¹⁾	./.	./.	./.	--	--	--	./.	./.	./.	--	--	--	s
Appearance after test: burned out till max. height 13 cm x width 2,5 cm													

¹⁾ time mentioned from the beginning of the test ²⁾ during 20 Sec -/- no appearance -- no information

6. Remarks and explanations to the testing procedure - none -
7. Opinion concerning the dropping of burning material
The test for normal flammability shows no burning dripping material.

Prüfinstitut Hoch

Lerchenweg 1
D-97650 Fladungen
Tel.: 09778-7480-200, Fax: 09778-7480-209
notified body no.: 1508 Mitglied der 
hoch.fladungen@t-online.de www.brandverhalten.de



Prüfinstitut für das Brandverhalten von Bauprodukten, Dipl.-Ing. (FH) Andreas Hoch
Bauaufsichtlich anerkannte Prüf-, Überwachungs- und Zertifizierungsstelle

Prüfinstitut Hoch, Lerchenweg 1, D-97650 Fladungen

Junkers & Müllers GmbH

z. Hd. z. Hd. Frau Dr. Petra Tschöpe
Bolksbuscher Straße 27

D-41239 Mönchengladbach

Tel.: 02166-3939-164

Fax: 02166-390980

Petra.Tschoepe@jm-textile.com

Fladungen, den 10. Februar 2014

Durchwahl: 09778-7480-

Andreas Hoch: -201
Jürgen Hammer: -204
Thomas Peter: -205
Tina Zitzmann: -206
Christina Kümmerth: -207
Diana Günzel: -202

Brandprüfungen nach DIN 4102-1

PN 18740: „TT MEDIATEX BERMUDA SE“

-Polyestergewebe, einseitig mit Polymerbeschichtung und zusätzlicher Schutzbeschichtung- / Farbe: weiß

Seite B: beschichtete Seite

Von der Prüfstelle ermittelte Kennwerte:

Dicke $\approx 0,40$ mm / Flächengewicht ≈ 287 g/m²

PN 18738: „TT MEDIATEX JM-AIR EFFECT FR“

-Polyestergewebe, einseitig mit Polymerbeschichtung und zusätzlicher Schutzbeschichtung mit Perl pigment- / Farbe: weiß / silber-glänzend

Seite A: weiß / Seite B: silber-glänzend

Von der Prüfstelle ermittelte Kennwerte:

Dicke $\approx 0,36$ mm / Flächengewicht ≈ 228 g/m²

Sehr geehrte Frau Dr. Tschöpe,
mit dieser Post senden wir Ihnen

- das Prüfzeugnis PZ-Hoch-140145 für „TT MEDIATEX BERMUDA SE“ in Deutsch und Englisch
- das Prüfzeugnis PZ-Hoch-140153 für „TT MEDIATEX JM-AIR EFFECT FR“ in Deutsch und Englisch, sowie
- die dazugehörige Rechnung R14-107

Bei Rückfragen setzen Sie sich gerne mit uns in Verbindung.

Mit freundlichen Grüßen aus der Rhön