

Außenstelle Erwitte · Auf den Thränen 2 · 59597 Erwitte · Telefon (02943) 897-0 · Telefax (02943) 897 33 · E-Mail: erwitte@mpanrw.de

Report of the classification of the reaction to fire performance

No. 231001163-8

issued 06.04.2021

English version

Sponsor

Antalis 8, rue de Seine

92 100 Boulogne-Billancourt France

(submitted for testing by another sponsor*)

Order

Classification of the reaction to fire performance according to DIN EN 13501-1:2019-05

Date of order: 16.02.2021

Identification number of the notified testing institute: 0432

Name of the classified product:

White, semi-transparent, self-adhesive polyester fabric "Coala Organza" (submitted for testing by another name*)

*Information on this can be found in the file of MPA NRW

This report gives the classification of the above-mentioned building product in accordance to the procedure given in DIN EN 13501-1.

Publishing and copying of classification reports without permission of the MPA NRW is only allowed without any changes of the content and the form of the reports.

The shortened reproduction of classification reports needs the permission of the MPA NRW.

This classification report consists of 3 pages.



1 Description of the building product

White, semi-transparent polyester fabric with an acrylate-based adhesive coating on one side

Mass per unit area of the fabric: 95 g/m²

Thickness of the fabric: 245 µm

2. Test reports and test results supporting the classification

2.1 Test reports

Name of the test laboratory	Sponsor	No. of the test report	Test procedure
MPA NRW	submitted for testing by another sponsor	231001163-1 of 06.04.21 231001163-2 of 06.04.21	DIN EN ISO 11925 – 2 DIN EN 13823

2.2 Test results

The following test results are the basis of the classification

	Parameter	Number of tests per-formed	Test results	
Test method			Average values of continously parameter	Requirements of diskrete parameter
DIN EN ISO 11925-2 30 s flaming time	Flamespread ≤150 mm Burning droplets/particles	12		yes no
	FIGRA _{0.2} in W/s		0	
	FIGRA _{0.4} in W/s		0	
	THR _{600s} in MJ		0,4	
DIN EN 13823	LFS _{edge}	3		< edge
DIN EN 13023	SMOGRA in m²/s²	3	0	
	TSP _{600s} in m ²		13	
	Duration of burning droplets/particles in s	,	0	



3. Classification and direct field of application

3.1 Reference

This classification was carried out in accordance to the clauses 11 and 14 of the standard DIN EN 13501-1:2019-05.

3.2 Classification

The tested building product in relation to its reaction to fire behaviour is classified as:

The additional classification in relation to smoke production is: s1

The additional classification in relation to flaming droplets/particles is:

The classification of the reaction to fire performance is therefore:

Fire behaviour	Smoke devel- opment	Flaming droplets
В	s1	d0

i. e. **B - s1,d0**

3.3 Field of application of the product

The classification is valid solely for the product described in clause 1 for the application on glass substrate.

4. Restrictions

This classification report does not represent type approval or certification of the product.

5. Remark

This classification report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is valid solely.

Erwitte, 06.04.2021

On behalf

Dipl.-Ing. Rademacher

Head of notified testing body

Dipl.-Ing. Schreiner

Engineer in charge

Date of issue of this English version: 06.04.2021