



Common Attributes	Units	Test Method	120gsm	160gsm	250gsm	400gsm
Wood Pulp Bleach Type			100% Cotton			
Printing Process Suitability						
Mono Laser Guaranteed '!'			✓	✓	✓	✓
Colour Laser Guaranteed			✓	✓	✓	✓
Mono Ink Jet Guaranteed '!'			✓	✓	✓	✓
Colour Ink Jet Guaranteed			✓	✓	✓	✓
THP?						
Recommended p.H. of Fount solution						
Non Aging Credentials		ISO 9706	yes			
Environmental Label		ISO 14001	yes			
Quality Management		ISO 9002	yes			
Moisture Content	%	ISO 287	6.5 (Wet 5.5)	6,5	6,5	6,5
Relative Humidity	%	TAPPI T502	40-60 (Wet 30-40)	40-60	40-60	40-60

Arches

Caliper	µm	ISO534	210	250	400	620
Bright White Opacity	%	ISO2471	92	94	96	
Bendtsen Roughness	ml/min	ISO2494	600	>1200	>1200	>1200
Taber Stiffness M Direction	mN	ISO2493	8.6	17.3	57	166
C Direction			4.0	9.0	32	103

'!' Arches papers are inkjet or laser guaranteed but Arches papers are compatible. Acceptable results can be achieved on some machines so please trial before purchase.

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. They are target values only for use as a guide.