

UPM Raflatac Technical Information

09-12-2020 EN SI

| | |
|----------------|---|
| Product | CASTGLOSS NXT+FSC / PERM.GREENTAC + / KRAFT SPECIAL 83-FSC / SCORE PRINTED |
| Sales Code | GNY/SP34/EJB/W3 |
| Product use | Product designed for high-quality labels with multicolour printing and a mirror-like high-gloss finish. Especially recommended for product and promotional labeling. The RAFNXT+ product design results in a superior carbon performance by leveraging a smarter choice and use of materials. |

Typical technical values

| | |
|---------------------|--|
| Face | CASTGLOSS NXT+FSC |
| Product | Cast coated, woodfree paper with mirror-like gloss finish. |
| Substance | 80 g/m ² ISO 536 |
| Caliper | 78 µm ISO 534 |
| Tensile strength MD | 5 kN/m ISO 1924/1 |
| Tensile strength CD | 2.9 kN/m ISO 1924/1 |
| Brightness | 87 % ISO 2470/1 |
| Roughness | 0.7 µm ISO 8791 |
| Opacity | 88 % ISO 2471 |
| Gloss | 89 % Hunter 75° |
| Stiffness MD | 0.42 mNm ISO/DP 2493 |
| Stiffness CD | 0.25 mNm ISO/DP 2493 |
| Printability | Flexography, letterpress, rotogravure, offset, screen and hot foil. |
| Sustainability | The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCHCOC-004879. |
| Adhesive | SP34 GREENTAC PLUS |
| Type | General permanent adhesive for sheets. |
| Composition | Modified acrylic dispersion. |
| Tack min | 10 N FTM 9 |
| Shear min | 2 h FTM 8 |
| Backing | KRAFT SPECIAL 83-FSC |
| Product | White woodfree kraft backing paper |
| Substance | 83 g/m ² ISO 536 |
| Caliper | 84 µm ISO 534 |
| Tensile strength MD | 8.7 kN/m ISO 1924 |
| Tensile strength CD | 3.8 kN/m ISO 1924 |
| Sustainability | The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCHCOC-004879. |



Performance

| | |
|-------------------------------|--|
| Total caliper | 181 µm |
| Minimum labelling temperature | 5 °C |
| Service temperature | - 10 - 100 °C |
| Shelf life | From date of manufacture: 48 months, under FINAT defined storage conditions (+20-25°C and 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life. |

Information

| | |
|---------------------|---|
| Product Information | Scoring is crucial to ensuring self-adhesive labels are easily peeled away from their backing. Our sheets have folding scores that are spaced at 35 mm intervals, what enables a smooth label opening. Scores open after bending 90–120° Scores don't open if they have not been folded previously. |
|---------------------|---|

Approvals

| | |
|------------|---|
| Approvals | For further compliance information related to food labeling applications, please contact your local sales representative for a Declaration of Conformance (DoC) document. |
| Approvals | Toy labeling: This product complies with the European Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements. |
| Disclaimer | The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market. |

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

