teattolour teartolour teatholour to THE teartolour teatholour teartolour to CREATIVE CREATIVE SHER teatholour teattolour teatholour to CREATIVE teartolour teartolour teartolour CREATIVE CREATIVE CREATIVE tearta/ tearts, tearts,

byant

byank

byank

to

byant

ter

With a chromatically rich colour pallet ranging from 120 up to 450gsm, Keaykolour enables you to answer all your customers' needs, from corporate identity, creative applications to luxury packaging.

Also available in digital format Keaykolour gives you endless possibilities to let your imagination and creativity run wild.

Unleash your creativity with the 45 shades of Keaykolour!

COLOURS CATEGORIES

WHITES China White, Pure White, Snow White	WHITES	China White.	Pure White.	Snow White
--	--------	--------------	-------------	------------

PASTELS Biscuit, Pastel Blue, Pastel Green, Pastel Pink

Albatross, Atoll, Azure, Baltic Sea, Basalt, Blackberry, Camel, Cappuccino, Caribbean Blue, Carmine, Chalk, Chili Pepper, Cobblestone, Coral, Deep Black, Grey Fog, Guardsman Red, Holly, Indian Yellow, Kiwi, Lichen, Lipstick,

Matcha Tea, Meadow, Navy Blue, Old Rose, Orchid, Parchment grey,

Parchment Natural, Port Wine, Prune, Pumpkin, Rosebud, Royal Blue, Seal,

Sequoia, Sombre Grey, Steel













Printing Guidelines

Design and pre-press

A screen of 133-150 lpi should be used. Finer screen up to a maximum of 200 lpi can also give very good results with careful ink density control. For dark 4-colour images with high ink density, under colour removal may be required depending on the visuals. Aim for the total ink film weight of 260%.

Offset litho printing

For optimum results on boards increase the blanket pressure or us a softer blanket to achieve consistent ink lay down.

Printing inks

Conventional positive drying inks should be used with or without infra-red drying assistance. Oxidizing inks or UV inks may also be used. Avoid using overnight / stay fresh / duct stable inks. Allow sufficient drying time. Use laser stable inks for subsequent laser printing. Consult your ink supplier about specific projects to ensure ink suitability.

Paper handling

To avoid marking and set-off when printing multiple colours, 35μ anti set-off spay for boards and 20μ for paper weights are recommended. Turn off the delivery stack jogger and restrict the delivery pile when printing boards. Always protect paper from environmental humidity and temperature changes by using stack cover or stretch wrap.

Sealer and coatings

They can be used to reduce marking for further operation. Ensure the inks are suitable and best result are achieve when the inks are dry before sealing.

Varnishing

For a gloss varnish, it is essential to pre-seal the surface with silk screen applied matt UV varnish, followed by subsequent applications of gloss UV varnish to achieve the desired effect. Ensure suitable inks are used prior to varnishing and that the inks are completely dry before varnish application. Not recommended for paper weights. Consider a clear hot foil as an alternative.

Hot foil stamping and Thermography

Keaykolour accepts hot foil stamping easily. We recommend to trial thermography before production.

Die Stamping and Blind embossing

Keaykolour can be die stamped with superior result and very detailed imagery. It can also be blind embossed, we recommend to have the corners of the die rounded off to help prevent creases forming from them.

Die and laser cutting

Keaykolour paper and boards can be die cut. While laser cutting some scorching will be apparent around the cut area. Laser cut papers are more prone to miss-feeds and jams within office printing technologies.

Binding and adhesives

Standard adhesives and binding techniques can be used.

Office Printing

Low weight Keaykolour papers often give acceptable results for text and simple graphic application.

Digital technologies

Keaykolour is suitable for Dry Toner and Keaykolour Digital is certified for HP Indigo printing (certification pending for Keaykolour Holly).













WHITES

Dry Toner ®

Property & Unit	Standard					
GSM	ISO 536	120	170	250	300	450
Caliper (μm)	TAPPI T411	170	240	350	405	610
Bendtsen roughness [felt/ wire] (ml/min)	TAPPI T538	850 / 600	1000 / 750	1200 / 800	1200 / 850	1400 / 1400
Stiffness MD (mN)	ISO 5628:2493	25	75	250	420	1300
Stiffness CD (mN)	ISO 5628:2493	15	30	120	190	560
Moisture content (%)	TAPPI T412	7.0				
Relative humidity (%)	TAPPI T415	30 - 60				

 $[\]star$ For further information regarding the HP Indigo certified items, please refer to Keaykolour Digital data sheet













PASTELS

Dry Toner ®

Property & Unit	Standard			
GSM	ISO 536	120	300	
Caliper (µm)	TAPPI T411	160	405	
Bendtsen roughness [felt/ wire] (ml/min)	TAPPI T538	600 / 450	1000 / 750	
Stiffness MD (mN)	ISO 5628:2493	21	355	
Stiffness CD (mN)	ISO 5628:2493	12	172	
Moisture content (%)	TAPPI T412	7.0		
Relative humidity (%)	TAPPI T415	30 - 60		













Dry Toner ®

Property & Unit	Standard					
GSM	ISO 536	120	170	250	300	450
Caliper (μm)	TAPPI T411	170	240	350	440	610
Bendtsen roughness [felt/ wire] (ml/min)	TAPPI T538	850 / 600	1000 / 750	1200 / 800	1200/850	1400 / 1400
Stiffness MD (mN)	ISO 5628:2493	25	75	250	420	1300
Stiffness CD (mN)	ISO 5628:2493	15	30	120	190	560
Moisture content (%)	TAPPI T412	7.0				
Relative humidity (%)	TAPPI T415	30 - 60				

 $[\]star$ For further information regarding the HP Indigo certified items, please refer to Keaykolour Digital data sheet













PARCHMENT

Dry Toner ®

Property & Unit	Standard				
GSM	ISO 536	120	170	300	
Caliper (µm)	TAPPI T411	170	240	420	
Bendtsen roughness [felt/ wire] (ml/min)	TAPPI T538	850 / 600	1000 / 750	2500/2500	
Stiffness MD (mN)	ISO 5628:2493	25	75	415	
Stiffness CD (mN)	ISO 5628:2493	15	30	160	
Moisture content (%)	TAPPI T412	7.0			
Relative humidity (%)	TAPPI T415	30 - 60			











