

Opale[®]



Common attributes	Test method	80g	90g	100g	120g	150g	250g	300g	
Wood pulp & bleach type		ECF Woodfree Virgin Pulp - FSC certified							
Printing process suitability		Opale Reference Recycled has 50% post-consumer waste							
Mono laser guaranteed		Yes				No			
Colour laser guaranteed		Yes				No			
Mono ink jet guaranteed		Yes				No			
Colour ink jet guaranteed		Yes				No			
Recommended pH of fount solution		5.5 +/- 0.5							
Surface pH	TAPPI 529QM	5							
Non aging credentials	ISO 9706	No							
Environmental label	ISO 14001	Yes							
Quality management	ISO 9001:2000	Yes							
Moisture content (%)	ISO 287	6							
Relative humidity (%)	TAPPI T502	40 - 60							

Premier Wove

Caliper (µm)	ISO 536	-	-	110	126	-	254	300	
Bulk µ/(gm ²)	ISO 534	-	-	1,05	1,06	-	1,00	1	
Smoothness (ml/min)	ISO 5627	-	-	100	100	-	60	60	
Whitest shade opacity (%)	ISO 2471	-	-	89,5	92	-	-	-	
ISO Whiteness (%)	ISO 2470	-	-	115	115	-	115	115	
Moisture content (%)	ISO 287	-	-	5	5	-	7	7	
Stiffness (mN)	M direction	ISO 2493	-	-	0,40	0,40	-	32	28
	C direction		-	-	0,30	0,30	-	17	20

Reference Wove, Reference 50% Recycled

Caliper (µm)	ISO 536	91	99	108	-	-	254	300	
Bulk µ/(gm ²)	ISO 534	1,15	1,10	1,08	-	-	1,00	1,00	
Smoothness (ml/min)	ISO 5627	100	80	100	-	-	60	60	
Whitest shade opacity (%)	ISO 2471	87	88	89	-	-	-	-	
ISO Whiteness Wove (%)	ISO 2470	115	-	115	-	-	115	115	
ISO Whiteness Recycled (%)		-	102,4	-	-	-	-	-	
Moisture content (%)	ISO 287	5,8	6,5	5,8	-	-	7	7	
Stiffness (mN)	M direction	ISO 2493	0,37	0,37	0,40	-	-	32	28
	C direction		0,19	0,19	0,30	-	-	17	20

Reference Fabric

Caliper (µm)	ISO 536	-	-	145	-	-	310	-
Bulk µ/(gm ²)	ISO 534	-	-	1,45	-	-	1,24	-
Whitest shade opacity (%)	ISO 2471	-	-	89	-	-	-	-
ISO Whiteness (%)	ISO 2470	-	-	115	-	-	115	-
Moisture content (%)	ISO 287	-	-	5,5	-	-	7	-

Please note: Due to the texturing process it is not possible to give accurate figures for roughness and stiffness for Reference Fabric.

Dialogue Wove

Caliper (µm)	ISO 536	-	103	-	137	162	-	-	
Bulk µ/(gm ²)	ISO 534	-	1,14	-	1,14	1,08	-	-	
Smoothness (ml/min)	ISO 5627	-	75	-	75	75	-	-	
Whitest shade opacity (%)	ISO 2471	-	87	-	90	93	-	-	
ISO Whiteness (%)	ISO 2470	-	115	-	115	115	-	-	
Moisture content (%)	ISO 287	-	4,5	-	4,5	4,5	-	-	
Stiffness (mN)	M direction	ISO 2493	-	0,39	-	0,39	2	-	-
	C direction		-	0,25	-	0,25	1	-	-

These specifications are the property of Arjowiggins Creative Papers and may be changed without prior notice.

They are target values only for use as a guide.

