



Pop'Set®

Technical Sheet

Common Attributes	Units	Test Method	80gsm	90gsm	100gsm	120gsm	135gsm	170gsm	240gsm	320gsm	400gsm
Wood Pulp Bleach Type			ECF Woodfree Virgin Pulp, 30% Recycled								
Printing Process Suitability			Litho, Silk Screen, Dry Offset (Toray), Blind Embossing, (Hot Foil Blocking, Die Stamping)								
Mono Ink Jet Guaranteed			✓	✓	✓	✓	✓	✓	✗	✗	✗
Colour Ink Jet Guaranteed			✓	✓	✓	✓	✓	✓	✗	✗	✗
Recommended p.H. of Fount solution		TAPPI 529OM	5.5 +/- 0.5								
Surface p.H.			5 for colours and 7.5 for Brilliant White, Oyster and Ivory								
Non Aging Credentials			Brilliant White, Oyster and Ivoryy are long life								
Environmental Label			Yes								
Quality Management			Yes								
Moisture Content		ISO 287	7	7	7	7	7	7	7	7	7
Relative Humidity		TAPPI T502	40-60	40-60	40-60	40-60	40-60	40-60	40-60	40-60	40-60
Caliper	µm	ISO534	98	110	123	147	160	200	300	380	490
Brilliant White Opacity	%	ISO2471	83,0	84,5	87,0	91,0	92,5				
Bendtsen Roughness	ml/min	ISO2494	250	250	250	250	250	320	320	320	350
Taber Stiffness M Direction	mN	ISO2493	4.3	7.0	10.0	25.0	30.0	47.0	135.0	275.0	415.0
C Direction			2.3	4.0	5.0	14.0	19.0	23.0	70.0	140.0	200.0

Note: The vivid colors Cosmo Pink and Ultra Red have a low level of light fastness (ISO 105 B02)

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. They are target values only for use as a guide.