

Sensation[®] Rives

GLOSS

Common Attributes	Units	Test Method	120gsm	170gsm	270gsm
Wood Pulp Bleach Type			ECF Woodfree Virgin Pulp - FSC Certified		
Printing Process Suitability			Litho, Silk Screen, Dry Offset (Toray), Blind Embossing, (Hot Foil Blocking, Die Stamping - image and paper texture depending)		
Mono Laser Guaranteed			trial	x	x
Colour Laser Guaranteed			trial	x	x
Mono Ink Jet Guaranteed			trial	trial	x
Colour Ink Jet Guaranteed			trial	trial	x
Recommended p.H. of Fount solution			5.5 +/- 0.5		
Surface p.H.		TAPPI 529OM	7,5		
Non Aging Credentials		ISO 9706	Yes		
Environmental Label		ISO 14001	Yes		
Quality Management		ISO 9001:2000	Yes		
Moisture Content	%	ISO 287	6,5	6,5	6,5
Relative Humidity	%	TAPPI T502	40-60	40-60	40-60

Tradition

Caliper	µm	ISO534	160	230	370
Bright White Opacity	%	ISO2471	94	97	99
Bendtsen Roughness	ml/min	ISO2494	900	900	1500
Kodak Stiffness M Direction	mN	ISO5629	1.2 0.6	3.5 2.5	18 9

Linear

Caliper	µm	ISO534	160	230	370
Bright White Opacity	%	ISO2471	94	97	99
Bendtsen Roughness	ml/min	ISO2494	900	900	1500
Kodak Stiffness M Direction	mN	ISO5629	1.2 0.6	3.5 2.5	18 9

Tactile

Caliper	µm	ISO534	155	220	370
Bright White Opacity	%	ISO2471	94	97	99
Bendtsen Roughness	ml/min	ISO2494	400	400	600
Kodak Stiffness M Direction	mN	ISO5629	1.2 0.6	3.5 2.5	18 9

Shetland

Caliper	µm	ISO534	160	230	370
Bright White Opacity	%	ISO2471	94	97	99
Bendtsen Roughness	ml/min	ISO2494	400	600	600
Kodak Stiffness M Direction	mN	ISO5629	1.2 0.6	3.5 2.5	18 9

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. The target values only for use as a guide.

ay are