

DuPont™ Tyvek® 1073D

Product Properties – Metric Units



Product Features:
Antistatic Treatment
Corona Treated

Product Properties – Metric Units

Property	Test Method	Unit	Typical Values
Basis Weight	ASTM D3776 ¹	g/m ²	75
Delamination	ASTM D2724 ²	N	>1.1
Elmendorf Tear, MD	EN 21974	N	>2.5
Elmendorf Tear, CD	EN 21974	N	>2.5
Tensile Strength, MD	EN 1924-2 ³	N	>180
Tensile Strength, CD	EN 1924-2 ³	N	>180
Elongation, MD	EN 1924-2 ³	%	21
Elongation, CD	EN 1924-2 ³	%	23
Thickness	DIN EN ISO 534 ⁴	µm	210
Opacity	ISO 2471 ⁵	%	96

Note: Typical values are based on mill roll averages with samples taken uniformly across the sheet

MD = machine direction; CD = cross direction.

1. Sample size 929.03 cm², modified for conditioning
2. Modified for: width = 25.4mm and speed = 127 mm/min
3. Modified for: speed = 100mm/min and gauge length = 127mm, width = 25.4mm
4. Surface 2 cm², pressure 50 kPa
5. Modified for: backing standards, measuring area and illumination = wide area

For more information, connect with us at: www.graphics.dupont.com

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark or technical information of DuPont or others covering any material or its use.

©2024 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.



DuPont™ Tyvek® 1073D

Product Properties – English Units

Product Features:
Antistatic Treatment
Corona Treated

Product Properties – English Units

Property	Test Method	Unit	Typical Values
Basis Weight	ASTM D3776 ¹	oz/yd ²	2.2
Delamination	ASTM D2724 ²	lbf	>0.25
Elmendorf Tear, MD	EN 21974	lbf	>0.56
Elmendorf Tear, CD	EN 21974	lbf	>0.56
Tensile Strength, MD	EN 1924-2 ³	lbf	>40.5
Tensile Strength, CD	EN 1924-2 ³	lbf	>40.5
Elongation, MD	EN 1924-2 ³	%	21
Elongation, CD	EN 1924-2 ³	%	23
Thickness	DIN EN ISO 534 ⁴	mils	8.3
Opacity	ISO 2471 ⁵	%	96

Note: Typical values are based on mill roll averages with samples taken uniformly across the sheet

MD = machine direction; CD = cross direction.

1. Sample size 929.03 cm², modified for conditioning
2. Modified for: width = 25.4mm and speed = 127 mm/min
3. Modified for: speed = 100mm/min and gauge length = 127mm, width = 25.4mm
4. Surface 2 cm², pressure 50 kPa
5. Modified for: backing standards, measuring area and illumination = wide area

For more information, connect with us at: www.graphics.dupont.com

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark or technical information of DuPont or others covering any material or its use.

©2024 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.