

## RUBAN ADHESIF POLYPROPYLENE SCOTCH

Item codes Antalis

585245

25 / 09 / 2024



### CHARACTERISTICS

|                   |                                                                                                                            |
|-------------------|----------------------------------------------------------------------------------------------------------------------------|
| DESCRIPTION       | <ul style="list-style-type: none"> <li>Ruban adhésif Polypropylène</li> <li>Scotch 3M 313</li> </ul>                       |
| MATERIAL          | <ul style="list-style-type: none"> <li>Polypropylene transparent</li> <li>Acrylique</li> <li>Boîte de 36 pièces</li> </ul> |
| ADVANTAGES        | <ul style="list-style-type: none"> <li>Très bonne tenue au froid.</li> </ul>                                               |
| APPLICATION AREAS | <ul style="list-style-type: none"> <li>Recommandé pour la fermeture de colis légers à lourds.</li> </ul>                   |

## RUBAN ADHESIF POLYPROPYLENE SCOTCH

### TECHNICAL DATA

| SPECIFICATION            | STANDARD | VALUE                   | UNIT   |
|--------------------------|----------|-------------------------|--------|
| Matière                  | -        | Polypropylene / hotmelt | -      |
| Couleur                  | -        | Transparent             | -      |
| Largeur totale           | -        | 48                      | mm     |
| Longueur totale          | -        | 100                     | m      |
| Epaisseur du support     | -        | 40                      | µm     |
| Epaisseur totale         | -        | 65                      | µm     |
| Type d'adhésif           | -        | Acrylique               | -      |
| Adhésion sur acier       | -        | 330                     | cN/cm  |
| Résistance à la traction | -        | 6.13                    | daN/cm |
| Allongement à la rupture | -        | 165                     | %      |

#### REGARDING TOLERANCES

All Technical data provided are average values.  
 Very slight variations are possible due to material tolerances.  
 We advise to test the required material to ensure suitability for intended application.

All specifications of Antalis supplied products are confidential and may not be forwarded to third parties without written consent of Antalis.