

# PAPIER KRAFT ADOUR NATUREL

Item codes Antalis

**306310**

09 / 2023



## CHARACTERISTICS

<b>DESCRIPTION</b>	<ul style="list-style-type: none"> <li>Papier Kraft Adour naturel</li> </ul>
<b>MATERIAL</b>	<ul style="list-style-type: none"> <li>Kraft Adour naturel</li> <li>Blond</li> <li>Grammage: 90 g / m<sup>2</sup></li> <li>Dimensions: 650 mm x 920 mm</li> </ul>
<b>ADVANTAGES</b>	<ul style="list-style-type: none"> <li>Certifié 100 % PEFC</li> <li>Papier recycle, réutilisable et recyclable, certifié PEFC</li> <li>Excellente résistance à la déchirure</li> <li>Aspect esthétique pour valoriser vos produits</li> </ul>
<b>APPLICATION AREAS</b>	<ul style="list-style-type: none"> <li>Pour l’emballage et la protection de vos produits</li> <li>Pour le calage et le remplissage de vide de vos colis</li> <li>Utilisation en intercalaire de palettisation</li> <li>Vendu par paquet de 250 feuilles</li> </ul>

# PAPIER KRAFT ADOUR NATUREL

## TECHNICAL DATA

SPECIFICATION	STANDARD	VALUE	UNIT
Epaisseur	-	113	µm
Volume massique	-	1.26	cm <sup>3</sup> /g
Absorption eau COBB 60R°	-	27	g/m <sup>2</sup>
Resistance à la traction SM	-	6.45	kN/m
Resistance à la traction ST	-	3.36	kN/m
Longueur de rupture SM	-	7300	m
Longueur de rupture ST	-	3800	m
Resistance à l'éclatement	-	279	kPa
Humidité Moyenne	-	7.7	%

### EXPLANATION VALUES USED IN TABLE

All above values are typical values at conditioning atmosphere XX% and XX°C according to ISO-standards.

- ISO 536
- ISO 534
- ISO 5636/3

### REGARDING TOLERANCES

All Technical data provided are average values.  
 Very slight variations are possible due to material tolerances.  
 We advise to test the required material to ensure suitability for intended application.

All specifications of Antalis supplied products are confidential and may not be forwarded to third parties without written consent of Antalis.